

# STIC-ADHESIVE Products Co., Inc.

3950 Medford Street  
Los Angeles, California 90063  
(323) 268-2956 • Fax (323) 268-6480  
www.sticadhesive.com

## Technical Data Sheet

### STIC-KOTE 900 DTM Acrylic Paint, Primer (White)

03/2010

#### DESCRIPTION

STIC-KOTE 900 Primer is a low VOC, water-based, direct-to-metal primer for industrial and architectural applications. This product utilizes a modified-acrylic emulsion that provides protection against corrosion, weathering, and harsh environmental elements. It may be used on both exterior and interior surfaces, dries quickly, and is appropriate as a primer for most water-based paint finishes (see Recommended Usage).

This primer is intended for use on most prepared surfaces, including steel, aluminum, galvanized steel, masonry, wood, drywall and concrete. STIC-KOTE 900 DTM Primer is recommended to be used with STIC-KOTE 1800 series DTM Acrylic Paints.

#### APPLICATION PROPERTIES

- |  |  |
|--|--|
| 1) Volatile Organic Compound:<br>(VOC EPA Method 24) | < 120 g/L, 1.0 lb/gal                            |
| 2) Color:  | White<br>(available in most Fed Std. 595 colors) |
| 3) Finish:   | Flat   |
| 4) Weight Solids:                                    | 62% ± 2%   |
| 5) Volume Solids:                                    | 47% ± 2%   |

#### USE PROPERTIES

- |                             |  |
|-----------------------------|--|
| 1) Shelf Life:              | 3 years from date of manufacture (if unopened)<br>store indoors  |
| 2) Flash Point (SETA):      | > 212°F (100° C)   |
| 3) Reducer:                 | Water (do not use organic solvents)  |
| 4) Tinting:                 | Use standard commercially available tinting colors. Some tinting products can affect corrosion, adhesion, weathering, and other physical properties. Always test first. Use a mechanical shaker for at least 4-5 minutes to mix in the tint. |
| 5) Clean Up:                | Water (do not use organic solvents)  |
| 6) Application Equipment:   | Brush, roller, and airless or conventional spray   |
| 7) Application Temperature: | 50°-110°F (10°-43° C) for surface, paint and ambient air   |
| 8) Application Humidity:    | Maximum of 85% relative humidity   |
| 9) Storage:                 | Store product in accordance with local, state and federal regulations. Keep container tightly sealed and store indoors in dry conditions at 45°-100°F (7°-38°C).   |

# TECHNICAL DATA SHEET

## RECOMMENDED USAGE

Steel, Aluminum, Galvanized, Wood,  
Masonry & Concrete:

1 coat STIC-KOTE 900 DTM Primer, applied at 3-5 mils (75-125 microns) dry thickness; and  
1-2 coats STIC-KOTE 1800 Series DTM Paint, applied at 3-4 mils (75-100 microns) dry thickness. Note: 2 coats of top coat provides best protection.

Notes regarding Masonry & Concrete:

Best results if surface is smooth and without porous gaps. If necessary, prepare surface with mastic filler to cover gaps and holes.

## SURFACE PREPARATION

Surface must be clean, dry and in sound condition, free from loose mill scales, dirt, dust, rust, oil and grease. Remove all loose scales, peeling, flaking paint, rust, corrosion and chalk from the surface before painting.

- |                         |  |
|-------------------------|--|
| 1) Steel, Iron          | Hand-tool clean per SSPC-SP1 (removing all loose mill scale, loose rust, loose paint, and other foreign material)                    |
| 2) Galvanized, Aluminum | Solvent clean per SSPC-SP1 (removing oil, grease, dirt, and other soluble foreign material)  |
| 3) Masonry & Concrete   | Prepare surface to be clean and uniform per SSPC-SP13/NACE No. 6 (removing laitance, dust, loose concrete, and foreign contaminants) |

## RECOMMENDED COVERAGE PER COAT (DRY FILM)

1) Coverage	$\text{ft}^2/\text{gal}$	$\text{m}^2/\text{L}$
Minimum:	140 ± 20 sq.ft.	3.4 ± 0.5 sq. meters
Maximum:	233 ± 20 sq.ft.	5.7 ± 0.5 sq. meters
2) Wet Film Thickness per coat:	6 - 10 mils (min/max)	150 - 250 microns (min/max)
3) Dry Film Thickness per coat:	3 - 5 mils (min/max)	75 - 125 microns (min/max)
4) Theoretical Coverage of Dry Film:		
Dry film thickness	1 mil	700 $\text{ft}^2/\text{gal}$
Dry film thickness	25 micron	18 $\text{m}^2/\text{L}$

Note: Brush or roller application may require multiple coats to achieve maximum film thickness.

## RECOAT SCHEDULE @ 3 mil (75 microns) DRY FILM - 6 mil (150 microns) WET FILM

<b>Temperature:</b>	<b><math>50 \pm 10^\circ\text{F}</math></b> ( $10 \pm 5^\circ\text{C}$ )	<b><math>77 \pm 10^\circ\text{F}</math></b> ( $25 \pm 5^\circ\text{C}$ )
1) Touch Time:	1.5 hours	0.75 hour
2) Recoat Time:	8 hours	4 hours
3) Dry Hard Time:	20 Days	12 Days

# TECHNICAL DATA SHEET

## PERFORMANCE PROPERTIES

<u>Property</u>	<u>Test Method</u>	<u>Results</u>
Adhesion	ASTM D-3359	Excellent 5/5 (rating: 0-5 (5=best)) steel, aluminum
Flexibility	ASTM D-522	Passes
Impact Resistance	ASTM D-4226	>160 in/lb. direct and indirect impact
Corrosion, Rust, Adhesion, Humidity, Blistering, and Condensation Resistance	ASTM D-2247 (500 hours) ASTM D-610/D-714	Excellent 10/10 (rating: 0-10 (10=best))
Accelerated Weathering Resistance	ASTM D-4587; (1,000 hours) QUV	Passes with gloss retention >80%
Salt Spray	ASTM B117 (500 hours) ASTM D-610/D-714	Excellent 9/10 (rating: 0-10 (10=best))
Working Property	ASTM D-2932	Passes
Condition in Container	low temp: 40°F ± 3° (2 weeks) high temp: 100°F ± 3° (2 weeks)	Passes Passes

## SAFETY

Refer to the Material Safety Data Sheet (MSDS) before using this product, for safe use, handling and storage.

## OTHER INFORMATION

### HEALTH AND SAFETY INFORMATION:

Refer to Material Safety Data Sheet for health and safety information before using this product. Also, for additional information, please visit the website at [www.sticadhesive.com](http://www.sticadhesive.com).

### LIMITATION OF REMEDIES AND LIABILITY:

If the STIC-ADHESIVE product is proved to be defective, the exclusive remedy, at STIC-ADHESIVE'S option, shall be to refund the purchase price or replace the defective product. STIC-ADHESIVE shall not otherwise be liable for loss or damages, regardless of the legal theory, including but not limited to contract, negligence, warranty, or strict liability.

### DISCLAIMER:

The material in this Technical Data Sheet (TDS) is, to the best of our knowledge, accurate as of the date issued. However, neither STIC-ADHESIVE nor any of its subsidiaries or agents assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of suitability of any material is the sole responsibility of the user. Compliance with all applicable federal, state, and local laws and regulations remains the responsibility of the user. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that these are the only hazards that may exist. Given the quantity of variables that affect use and application of our products, many of which are within the user's control and unique to each user's knowledge, STIC-ADHESIVE MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE.